

Test Report # 19W-000985 Date of Report Issue: January 28, 2019
Date of Sample Received: January 16, 2019 Pages: Page 1 of 12

CLIENT INFORMATION:

Company: Cap America

Address: One Cap America Drive Fredericktown, MO 63645

USA

SAMPLE INFORMATION:

Description: 60% Cotton/ 40% Polyester Camo cap with 100% Polyester mesh back

SKU No.: i2006 AP
Style No.: i2006
PO No.: 78677
Factory/Supplier: JF
Quantity Submitted: 6 pcs

Country of Distribution: Canada, United States

Country of Origin: China

Testing Period: 01/22/2019-01/28/2019

OVERALL RESULT:

PASS with information

Refer to page 2 for test result summary and appropriate notes.

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

Kein.lee

Kevin Lee

Technical Manager

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

• Email: Labtesting@asiainspection.com

• Tel: (86)

• 5/F A2 Building
• No. 1213 Huoju South Road
• Puyan Street
• Binjiang District
• Hangzhou
• Ch

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.



Test Report # 19W-000985 Date of Report Issue: January 28, 2019

Date of Sample Received: January 16, 2019 Pages: Page 2 of 12

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	Model Toxics in Packaging Legislation of the Toxics in Packaging Clearinghouse (TPCH)
PASS	Appearance after Laundering
Refer to Detailed Results	Color Fastness to Perspiration
Refer to Detailed Results	Color Fastness to Crocking



Test Report # 19W-000985 Pages: Page 3 of 12

DETAILED RESULTS:

CPSIA Section 101, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3	4	5	6	7	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	8	9	10			Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND			100
Conclusion	PASS	PASS	PASS			

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Data Consolidation Reference:

Craciman Na	Transferre	Transferred from			
Specimen No.	Report No.	Specimen No.	Date of Issue		
3	19W-000978	6	January 28, 2019		
4	19W-000978	7	January 28, 2019		
5	19W-000978	4	January 28, 2019		
6	19W-000978	5	January 28, 2019		
7	19W-000983	6	January 28, 2019		
8	19W-000978	10	January 28, 2019		
9	19W-000978	11	January 28, 2019		



Test Report # 19W-000985 Pages: Page 4 of 12

DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal) Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3	4	5	6	7	Limit
Test Item	Result	Result	Result	Result	Result	(mg/kg)
Test item	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	8	9	10			Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND			100
Conclusion	PASS	PASS	PASS			

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Caccimon No	Transferre	Transferred from			
Specimen No.	Report No.	Specimen No.	Date of Issue		
3	19W-000978	6	January 28, 2019		
4	19W-000978	7	January 28, 2019		
5	19W-000978	4	January 28, 2019		
6	19W-000978	5	January 28, 2019		
7	19W-000983	6	January 28, 2019		
8	19W-000978	10	January 28, 2019		
9	19W-000978	11	January 28, 2019		



Test Report # 19W-000985 Pages: Page 5 of 12

DETAILED RESULTS:

Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3	4	5	6	7	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	8	9	10			Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND			90
Conclusion	PASS	PASS	PASS			

Note:

mg/kg=Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Data Consolidation Reference:

Specimen No.	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
3	19W-000978	6	January 28, 2019
4	19W-000978	7	January 28, 2019
5	19W-000978	4	January 28, 2019
6	19W-000978	5	January 28, 2019
7	19W-000983	6	January 28, 2019
8	19W-000978	10	January 28, 2019
9	19W-000978	11	January 28, 2019



Test Report # 19W-000985 Pages: Page 6 of 12

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen N	0.	3	4	7	8	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Consisson No	Transferre	Transferred from				
Specimen No.	Report No.	Specimen No.	Date of Issue			
3	19W-000978	6	January 28, 2019			
4	19W-000978	7	January 28, 2019			
7	19W-000983	6	January 28, 2019			
8	19W-000978	10	January 28, 2019			



Test Report # 19W-000985 Pages: Page 7 of 12

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		9	10			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND			1000
Conclusion		PASS	PASS			

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Cnasiman Na	Transferre	Data of leave		
Specimen No.	Report No.	Specimen No.	Date of Issue	
9	19W-000978	11	January 28, 2019	



Test Report # 19W-000985 Pages: Page 8 of 12

DETAILED RESULTS:

Model Toxics in Packaging Legislation of the Toxics in Packaging Clearinghouse (TPCH)

Test Method: US EPA 3052:1996 & USEPA 6010D:2014

US EPA 3060A:1996 & USEPA 7196A: 1992

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry,

Ultraviolet-Visible Spectrophotometry

Specimen No.	1	2				Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Cadmium (Cd)	ND	ND				
Chromium (VI) [Cr (VI)]	ND	ND				
Lead (Pb)	ND	ND				
Mercury (Hg)	ND	ND				
Sum	ND	ND				100
Conclusion	PASS	PASS				

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Data Consolidation Reference:

Craciman Na	Transferre	Data of Issue	
Specimen No.	Report No.	Specimen No.	Date of Issue
1	19W-000994	1	January 28, 2019
2	19W-000994	2	January 28, 2019



Test Report # 19W-000985 Pages: Page 9 of 12

DETAILED RESULTS:

Appearance after Laundering

Test Method: IHTM 002, observations on 3 cycles washed sample.

Specimen No.		11		
	Assessing Items	Result	Requirement	
1	Color Change	Negligible Change (Grade 4.5)	Min. 4.0	
2	Cross Staining	Negligible Change (Grade 4.5)	Min. 4.5	
3	Appearance of Print fabric	Negligible Change	Satisfactory	
4	Fuzzing /Pilling	Negligible surface fuzzing & pilling	Satisfactory	
5	Seam appearance	Negligible Change	Satisfactory	
6	Embroidery	Negligible Change	Satisfactory	
7	Buckle	Negligible Change	Satisfactory	
8	Shape	Negligible distortion	Satisfactory	
	Conclusion	PASS		

Remark:

- (1) Grey scale rating is based on the 5-step of 1 to 5, where 1 is bad and 5 is good.
- (2) Note: Washing procedure: AATCC TS-006: Hand wash at 85 °F, line dry.



Test Report # 19W-000985 Pages: Page 10 of 12

DETAILED RESULTS:

Color Fastness to Perspiration

Test Method: AATCC 15-2013(E2014)

Specimen No.	11			
Items	Client's requirement	Acidic Result (Grade)	Conclusion	
Change in shade	N/A	4.5		
Staining on multi-fiber stripe				
-Acetate	N/A	4.0		
-Cotton	N/A	4.5	Information only	
-Nylon	N/A	4.5		
-Polyester	N/A	4.5		
-Acrylic	N/A	4.5		
-Wool	N/A	4.5		
Cross staining	N/A	4.5		

Remark: Grey scale rating is based on the 5-step of 1 to 5, where 1 is bad and 5 is good.

Color Fastness to Crocking

Test Method: AATCC 8-2016

Specimen No.	11		
Items	Client's requirement	Result (Grade)	Conclusion
Dry staining	N/A	4.5	Information
Wet staining	N/A	3.0	only

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD • Email: Labtesting@asiainspection.com • Tel: (86 • 5/F A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • Ch

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.



Test Report # 19W-000985 Pages: Page 11 of 12

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	White plastic	Sling
2	Multi-color printed white paper	Hang tag
3	Black plastic	Brim
4	Black sponge	Sweatband
5	Silvery metal	Top button
6	Silvery metal	Top button base
7	Black printed white textile	Label
8	Transparent soft plastic	Inner thread
9	White plastic	Front surround
10	Black plastic	Tail band
11	Multi-color printed hat	Finished product



Test Report # 19W-000985 Pages: Page 12 of 12

SAMPLE PHOTO:





-End Report-