





17H-007246

TEST REPORT

Test Report # 17H-007246(R1) Date of Report Issue: September 20, 2017

Date of Sample Received: September 6, 2017 Pages: Page 1 of 12

CLIENT INFORMATION:

Company: BIC Graphic

Recipient: 14421 Myerlake Circle

Clearwater Florida 33760

United States (USA)

SAMPLE INFORMATION:

Description: Deluxe Desk Caddy Organizer

Assortment: - Purchase Order Number: 1624

Item No.: 32150 Country of Origin: China

Country of Distribution: United States, Canada Labeled Age Grade: -

Quantity Submitted: 2 pcs Recommended Age Grade: -

†Testing Period: 09/06/2017 – 09/12/2017 Tested Age Grade: -

09/18/2017 - 09/20/2017

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED



Loska Yeung Lok Ka Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report # 17H-007246(R1) Pages: Page 2 of 12

TEST RESULTS SUMMARY:

[†]At the request of the client, the following test was conducted:

| CONCLUSION | TEST(S) CONDUCTED |
|------------|--|
| PASS | California Proposition 65, Total Lead in Substrate Materials |
| PASS | California Proposition 65, Total Lead in Metal / Plastic / Textile |
| PASS | CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP) |
| PASS | California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP) |

Remark:

ANSECO GROUP (HK) LIMITED + 3/F Liven House + No. 61 – 63 King Yip Street + Kwun Tong + Kowloon + Hong Kong + Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

[†]Revised information and supersedes the previous Report no. 17H-007246.



Test Report # 17H-007246(R1) Pages: Page 3 of 12

DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

| Specimen No. | 1 | | | | | Total |
|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|----------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Limit (ppm) |
| Total Lead (Pb) | ND | | | | | 100 |
| Conclusion | PASS | | | | | |

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

SPECIMEN DESCRIPTION:

| Specimen No. | Specimen Description | Location | | |
|--------------|------------------------|------------------------|--|--|
| 1 | Brown/ grey paperboard | Brown paper desk caddy | | |

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report # 17H-007246(R1) Pages: Page 4 of 12

DETAILED RESULTS:

[†]California Proposition 65, Total Lead in Metal / Plastic / Textile

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

| Specimen No. | 2a | 2b | 3a | 3b | 4a | Total |
|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|----------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Limit (ppm) |
| Total Lead (Pb) | ND | ND | ND | ND | ND | 100 |
| Conclusion | PASS | PASS | PASS | PASS | PASS | |

| Specimen No. | 4b | 5a | 5b | 6a | 6b | Total |
|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|----------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Limit (ppm) |
| Total Lead (Pb) | ND | ND | ND | ND | ND | 100 |
| Conclusion | PASS | PASS | PASS | PASS | PASS | |

| Specimen No. | 7a | 7b | | | | Total |
|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|----------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Limit (ppm) |
| Total Lead (Pb) | ND | ND | | | | 100 |
| Conclusion | PASS | PASS | | | | |

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Specimen No. 3b (Metal paper clip with green PVC covering) is same material as Specimen No. 2b.

Specimen No. 4b (Metal paper clip with pink PVC covering) is same material as Specimen No. 2b.

Specimen No. 5b (Metal paper clip with yellow PVC covering) is same material as Specimen No. 2b.

Specimen No. 6b (Metal paper clip with white PVC covering) is same material as Specimen No. 2b.

Specimen No. 7b (Metal paper clip with red PVC covering) is same material as Specimen No. 2b.

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate #AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report # 17H-007246(R1) Pages: Page 5 of 12

[†]SPECIMEN DESCRIPTION:

| Specimen No. | Specimen Description | Location |
|--------------|----------------------|---|
| 2a | Blue PVC | Metal paper clip with light blue PVC |
| 2b | Silvery metal | covering Metal paper clip with light blue PVC covering |
| 3a | Green PVC | Metal paper clip with green PVC covering |
| 3b | Silvery metal | Metal paper clip with green PVC covering |
| 4a | Pink PVC | Metal paper clip with pink PVC covering |
| 4b | Silvery metal | Metal paper clip with pink PVC covering |
| 5a | Yellow PVC | Metal paper clip with yellow PVC covering |
| 5b | Silvery metal | Metal paper clip with yellow PVC covering |
| 6a | White PVC | Metal paper clip with white PVC covering |
| 6b | Silvery metal | Metal paper clip with white PVC covering |
| 7a | Red PVC | Metal paper clip with red PVC covering |
| 7b | Silvery metal | Metal paper clip with red PVC covering |

ANSECO GROUP (HK) LIMITED + 3/F Liven House + No. 61 – 63 King Yip Street + Kwun Tong + Kowloon + Hong Kong + Tel: (852)3185 8000



Test Report # 17H-007246(R1) Pages: Page 6 of 12

DETAILED RESULTS:

[†]CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

| Specimen No. | | 2a | 3a | 4a | 5a | |
|---------------------------------------|--------------------------|-----------------|-----------------|-----------------|-----------------|----------------|
| Test Item | CAS No. | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Limit (ppm) |
| Dibutyl phthalate (DBP) | 84-74-2 | ND | ND | ND | ND | 1000 |
| Benzyl butyl phthalate (BBP) | 85-68-7 | ND | ND | ND | ND | 1000 |
| Di-(2-ethylhexyl) phthalate (DEHP) | 117-81-7 | ND | 430 | ND | ND | 1000 |
| Di-n-octyl phthalate (DnOP) | 117-84-0 | ND | ND | ND | ND | 1000 |
| Diisononyl phthalate (DINP) | 28553-12-0 68515-48-0 | ND | ND | ND | ND | 1000 |
| Diisodecyl phthalate (DIDP) | 26761-40-0 68515-49-1 | ND | ND | ND | ND | 1000 |
| Conclusion | 1 | PASS | PASS | PASS | PASS | |

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 100 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

ANSECO GROUP (HK) LIMITED * 3/F Liven House * No. 61 – 63 King Yip Street * Kwun Tong * Kowloon * Hong Kong * Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report # 17H-007246(R1) Pages: Page 7 of 12

DETAILED RESULTS:

[†]CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

| Specimen No. | | 6a | 7a | | | |
|---------------------------------------|--------------------------|-----------------|-----------------|-----------------|-----------------|----------------|
| Test Item | CAS No. | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Limit (ppm) |
| Dibutyl phthalate (DBP) | 84-74-2 | ND | ND | | | 1000 |
| Benzyl butyl phthalate (BBP) | 85-68-7 | ND | ND | | | 1000 |
| Di-(2-ethylhexyl) phthalate (DEHP) | 117-81-7 | ND | ND | | | 1000 |
| Di-n-octyl phthalate (DnOP) | 117-84-0 | ND | ND | | | 1000 |
| Diisononyl phthalate (DINP) | 28553-12-0 68515-48-0 | ND | ND | | | 1000 |
| Diisodecyl phthalate (DIDP) | 26761-40-0 68515-49-1 | ND | ND | | | 1000 |
| Conclusion | | PASS | PASS | | | |

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 100 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

ANSECO GROUP (HK) LIMITED * 3/F Liven House * No. 61 – 63 King Yip Street * Kwun Tong * Kowloon * Hong Kong * Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report # 17H-007246(R1) Pages: Page 8 of 12

[†]SPECIMEN DESCRIPTION:

| Specimen No. | Specimen Description | Location |
|--------------|----------------------|---|
| 2a | Blue PVC | Metal paper clip with light blue PVC covering |
| 3a | Green PVC | Metal paper clip with green PVC covering |
| 4a | Pink PVC | Metal paper clip with pink PVC covering |
| 5a | Yellow PVC | Metal paper clip with yellow PVC covering |
| 6a | White PVC | Metal paper clip with white PVC covering |
| 7a | Red PVC | Metal paper clip with red PVC covering |

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000



Test Report # 17H-007246(R1) Pages: Page 9 of 12

DETAILED RESULTS:

[†]California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

| Specimen No. | | 2a | 3a | 4a | 5a | |
|---------------------------------------|--------------------------|-----------------|-----------------|-----------------|-----------------|----------------|
| Test Item | CAS No. | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Limit (ppm) |
| Dibutyl phthalate (DBP) | 84-74-2 | ND | ND | ND | ND | 1000 |
| Benzyl butyl phthalate (BBP) | 85-68-7 | ND | ND | ND | ND | 1000 |
| Di-(2-ethylhexyl) phthalate (DEHP) | 117-81-7 | ND | 430 | ND | ND | 1000 |
| Diisononyl phthalate (DINP) | 28553-12-0 68515-48-0 | ND | ND | ND | ND | 1000 |
| Diisodecyl phthalate (DIDP) | 26761-40-0 68515-49-1 | ND | ND | ND | ND | 1000 |
| Di-n-hexyl phthalate (DnHP) | 84-75-3 | ND | ND | ND | ND | 1000 |
| Conclusion | | PASS | PASS | PASS | PASS | |

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 100 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

ANSECO GROUP (HK) LIMITED * 3/F Liven House * No. 61 – 63 King Yip Street * Kwun Tong * Kowloon * Hong Kong * Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report # 17H-007246(R1) Pages: Page 10 of 12

DETAILED RESULTS:

[†]California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

| Specimen No. | | 6a | 7a | | | |
|---------------------------------------|--------------------------|-----------------|-----------------|-----------------|-----------------|----------------|
| Test Item | CAS No. | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Limit (ppm) |
| Dibutyl phthalate (DBP) | 84-74-2 | ND | ND | | | 1000 |
| Benzyl butyl phthalate (BBP) | 85-68-7 | ND | ND | | | 1000 |
| Di-(2-ethylhexyl) phthalate (DEHP) | 117-81-7 | ND | ND | | | 1000 |
| Diisononyl phthalate (DINP) | 28553-12-0 68515-48-0 | ND | ND | | | 1000 |
| Diisodecyl phthalate (DIDP) | 26761-40-0 68515-49-1 | ND | ND | | | 1000 |
| Di-n-hexyl phthalate (DnHP) | 84-75-3 | ND | ND | | | 1000 |
| Conclusion | 1 | PASS | PASS | | | |

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 100 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

ANSECO GROUP (HK) LIMITED * 3/F Liven House * No. 61 – 63 King Yip Street * Kwun Tong * Kowloon * Hong Kong * Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report # 17H-007246(R1) Pages: Page 11 of 12

[†]SPECIMEN DESCRIPTION:

| Specimen No. | Specimen Description | Location |
|--------------|----------------------|---|
| 2a | Blue PVC | Metal paper clip with light blue PVC covering |
| 3a | Green PVC | Metal paper clip with green PVC covering |
| 4a | Pink PVC | Metal paper clip with pink PVC covering |
| 5a | Yellow PVC | Metal paper clip with yellow PVC covering |
| 6a | White PVC | Metal paper clip with white PVC covering |
| 7a | Red PVC | Metal paper clip with red PVC covering |

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000



Test Report # 17H-007246(R1) Pages: Page 12 of 12

SAMPLE PHOTO:





-End Report-

ANSECO GROUP (HK) LIMITED + 3/F Liven House + No. 61 – 63 King Yip Street + Kwun Tong + Kowloon + Hong Kong + Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.