

TEST REPORT

Test Report #	16H-03078	Date of Report Issue:	June 7, 2016
Date of Sample Received:	June 1, 2016	Pages:	Page 1 of 6

CLIENT INFORMATION:

Company: BIC Graphic
 Recipient: 14421 Myerlake Circle
 Clearwater
 Florida
 33760
 United States (USA)



SAMPLE INFORMATION:

Description:	Premier Twist Pen		
Assortment:	-	Purchase Order Number:	7160
Item No.:	55031_CAR2	Country of Origin:	China
Country of Distribution:	United States, Canada	Labeled Age Grade:	-
Quantity Submitted:	5 pcs	Recommended Age Grade:	-
Testing Period:	06/03/2016 – 06/07/2016	Tested Age Grade:	-
		Previous Test Report #:	16H-01161

OVERALL RESULT:

 **PASS**

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED



Vincent Chow Wai Kit
 Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints & Surface Coatings
PASS	California Proposition 65, Total Lead in Paints & Surface Coatings
PASS	Canadian Toys Regulations (SOR/2011-17), Item 23 Total Lead and Mercury in Paints & Surface Coatings

DETAILED RESULTS:

CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints & Surface Coatings

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	25	---	---	---	---	90
Conclusion	PASS	---	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
2	Gray coating	Gray Coating on Gray metal pen

DETAILED RESULTS:

California Proposition 65, Total Lead in Paints & Surface Coatings

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	25	---	---	---	---	90
Conclusion	PASS	---	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
2	Gray coating	Gray Coating on Gray metal pen

DETAILED RESULTS:

Canadian Toys Regulations (SOR/2011-17), Item 23 Total Lead and Mercury in Paints & Surface Coatings

Test Method: ASTM F963-11 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	25	---	---	---	---	90
Total Mercury (Hg)	ND	---	---	---	---	10
Conclusion	PASS	---	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
2	Gray coating	Gray Coating on Gray metal pen

SAMPLE PHOTO:



-End Report-