



TEST REPORT

Test Report # 17H-004574
Date of Sample Received: June 8, 2017

Date of Report Issue: June 19, 2017
Pages: Page 1 of 11

CLIENT INFORMATION:

Company: BIC Graphic
Recipient: 14421 Myerlake Circle
Clearwater
Florida
33760
United States (USA)



SAMPLE INFORMATION:

Description:	Wave Runner Tote	Purchase Order Number:	1145
Assortment:	-	Country of Origin:	China
Item No.:	AP8630	Labeled Age Grade:	-
Country of Distribution:	United States, Canada	Recommended Age Grade:	-
Quantity Submitted:	3 pcs per style	Tested Age Grade:	-
Testing Period:	06/08/2017 – 06/19/2017		

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka
Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Metal / Plastic / Textile
PASS	CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

**DETAILED RESULTS:****California Proposition 65, Total Lead in Metal / Plastic / Textile**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	5	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	6	7	8	9	10	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	11	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	---	---	---	---	100
Conclusion	PASS	---	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Black/ gray/ light gray textile	Black/Gray webbing tab (all styles)
2	Silvery metal	Silver metal D-ring (all styles)
3	Light green textile with light green PVC backing	Apple Green fabric with backing (green style)
4	Dull grey textile with grey PVC backing	Charcoal fabric with backing (black style)
5	Orange textile with orange PVC backing	Orange fabric with backing (orange style)
6	Red textile with red PVC backing	Red fabric with backing (red style)
7	Blue textile with blue PVC backing	Royal fabric with backing (blue style)
8	White textile	White trim (all styles)
9	Dull black textile with PVC backing	Black fabric with backing (all styles)
10	Matt black textile	Black webbing handle (all styles)
11	Purple textile with purple PVC backing	Purple fabric with backing (purple style)

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street• Kwun Tong• Kowloon •Hong Kong •Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		3	4	5	6	
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 100 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		7	9	11	---	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 100 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
3	Light green textile with light green PVC backing	Apple Green fabric with backing (green style)
4	Dull grey textile with grey PVC backing	Charcoal fabric with backing (black style)
5	Orange textile with orange PVC backing	Orange fabric with backing (orange style)
6	Red textile with red PVC backing	Red fabric with backing (red style)
7	Blue textile with blue PVC backing	Royal fabric with backing (blue style)
9	Dull black textile with PVC backing	Black fabric with backing (all styles)
11	Purple textile with purple PVC backing	Purple fabric with backing (purple style)

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		3	4	5	6	
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 100 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		7	9	11	---	
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 100 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
3	Light green textile with light green PVC backing	Apple Green fabric with backing (green style)
4	Dull grey textile with grey PVC backing	Charcoal fabric with backing (black style)
5	Orange textile with orange PVC backing	Orange fabric with backing (orange style)
6	Red textile with red PVC backing	Red fabric with backing (red style)
7	Blue textile with blue PVC backing	Royal fabric with backing (blue style)
9	Dull black textile with PVC backing	Black fabric with backing (all styles)
11	Purple textile with purple PVC backing	Purple fabric with backing (purple style)



SAMPLE PHOTO:



-End Report-